

BTX 30057(1)/PS/05 Date: 6 June 2005

REPORT ON SUBMITTED SAMPLE RECEIVED ON 01 June 2005

Sample Description: White fabric

Test(s) requested: BS 7837:1996

Test results:

Date(s) of test Tested between 01/06/05 and 06/06/05

Flammability performance for textiles used in the construction of marquees and similar textile structures (BS 7837:1996)

The sample was tested after water soaking in accordance with clause 3 of BS 5651: 1989 followed by conditioning for not less than 24 hours in the prescribed atmosphere of 20±2°C and 65±5 % relative humidity. The test method used was BS 5438: 1989 Test 2B using a 10 seconds flame application time applied to bottom edge of the fabric and with the addition of the use of filter paper as described in clause 8.2 of this specification.

Requirements: The sample shall be deemed to pass it for at least five of six specimens have a duration of

flaming not exceeding 5 s after the removal of the igniting flame, the lowest boundary of any flame does not reach the upper or either vertical edge; and the filter paper does not

smoulder or flame.

Results: These results were obtained using the specified test conditions and do not necessarily

represent the behaviour of the test material under other conditions of test or use.

| Flame application time : 10 s | Length | | | Width | | |
|-------------------------------|--------|----|----|-------|----|-----|
| | 1 | 2 | 3 | 1 | 2 | 3 |
| Flame reached an edge : | No | No | No | No | No | No |
| Hole reached an edge : | No | No | No | No | No | No |
| Flaming debris : | No | No | No | No | No | No |
| Duration of flaming (s): | 0 | 0 | 0 | 3.9 | 7 | 3.7 |
| Duration of afterglow (s): | 0 | 0 | 0 | 0 | 0 | 0 |

Comments: The sample submitted complies with the requirements of BS 7837: 1996.

Paula Smith

Textile Technologist Softlines Department

All orders are accepted and all services are rendered subject to the General Conditions of Service available upon request and accessible at any time at www.sgs.com.

Attention is drawn to the limitations of liability, imdemnification and jurisdictional issues defined therein.

SGS United Kingdom Ltd

Oakwood House, City Road, Bradford BD8 8JY Tel +44 (0)1274 760400 Fax +44 (0)1274760429 Registered in England No. 1193985 Rossmore Business Park, Ellesmere Port, Cheshire, CH65 3E www.sgs.com